


RH-GP1100W

导热硅胶片 Thermal Gap Filler

Features and Benefits

特点与优势

- **High thermal conductivity: 14W/m-K 导热系数: 11W/M-K
- **※Excellent flame retardant**优秀的阻燃性



RH-GP1100W thermal conductive silicon film is very soft and well compressed, which is used to fill the interface of two items, so that the air of the interface is discharged and the heat conduction efficiency is improved. The product has self-adhesive, can be die-cut into various shapes, easy to assemble. Thermal conductivity: W/M.K.11

RH-GP1100W 导热硅胶片很柔软,很好压缩,用于填充两个物品的界面,使得界面的空气排出,提高导热效率。该产品有自粘性,可以模切成各种形状,容易装配。导热系数: 11W/M.K

The above suggestions and data are based on information that we believe to be reliable. Therefore, these suggestions and data are only for reference, not as product guarantee. It is up to the customer to decide whether the product is suitable or suitable for special use. We recommend that users first determine the suitability of our materials and recommendations before using them in large quantities.

以上建议及数据均来自我们认为可靠的资料。因此这些建议 及数据仅供参考,而不作为产品保证。应由客户决定产品是 否合适或适用特殊用途。我们建议用户在大量使用前,首先 确定我们的材料适用性和建议。

RH-GP1100W			
Property	Paramet er	Unit	Test Method
Color 颜色	浅灰色 Light Gray		Visual
Thermal Conductivity 导热系数	11	W/m.k	ASTM D5470
Percent Deflection @ Various Pressures (3mm thick sample) @ 34 kPa (5 psi)	9		ASTM C165 MOD (3mm,
@ 69 kPa (10 psi) @ 172 kPa (25 psi)	15 24	%	12.7mm dia. probe,0.5mm/
@ 345 kPa (50 psi) 压缩率 Hardness 硬度	34 60	Shore 00	min rate) ASTM D2240
Thickness 厚度 Density 密度	0.5-6.0 3.4	mm g/cc	ASTM D374 ASTM D792
Volume Resistivity 体积电阻率	1011	ohm-cm	ASTM D257
Dielectric Brekdown Voltage 击穿电压	>8	KV	ASTM D149
Thermal Impedance 热阻@ 10 psi, @ 1mm thick	1.0 (0.16)	C-cm2/W (°C-in2/W)	ASTM D5470
Fire Rating 防火等级	V-0		UL94
Working Temperature 工作温度 RoHS/REACH	-40~150 Compliance	°C 	

DII 004400VA

Applications

典型应用

Semiconductor heat sink半导体散热装置Graphics card, memory module显卡、记忆存储模块**Communication & power equipment通讯&电源设备**Vehicle navigator车载导航仪**LED television and lightingLED 电视和照明设备

Configurations Available

产品规格

Flake products: 300*400 mm or according to customer requirements

片状产品: 300*400mm 或依照顾客要求

*Die-cutting products: according to customer requirements

模切产品: 依照顾客要求

Storage & Transportation: store in a ventilated, cool and dry place, do not contact with open fire. This product is non-toxic and is stored and transported as non dangerous goods.

储存&运输:贮存于通风、阴凉、干燥处,不要接触明火。本产品无毒,按非危险品 贮存及运输。

Packaging: customized packaging according to customer needs.

包 装:根据客户需求定制包装。

Safety: please refer to material safety performance data (MSDS) of our company 安全:请参阅本公司《材料安全性能数据(MSDS)》

Period of validity: the product is valid for 12 months

有 效 期: 本产品有效期为 12 个月

深圳市睿玮新材料科技有限公司

电话 Tel: 0755 - 2340 0031 传真 Fax: 0755 - 3326 6039

