

RH-GP600

导热硅胶片 Thermal Gap Filler

Features and Benefits

特点与优势

- ∗High thermal conductivity: 6W/m-K

 字热系数: 6W/M-K
- **※Excellent flame retardant**优秀的阻燃性



RH-GP600 thermal conductive silicon film is very soft and well compressed, which is used to fill the interface of two items, so that the air of the interface is discharged and the heat conduction efficiency is improved. The product has self-adhesive, can be die-cut into various shapes, easy to assemble. Thermal conductivity: W/M.K.6

RH-GP600 导热硅胶片很柔软,很好压缩,用于填充两个物品的界面,使得界面的空气排出,提高导热效率。该产品有自粘性,可以模切成各种形状,容易装配。导热系数: 6W/M.K

The above suggestions and data are based on information that we believe to be reliable. Therefore, these suggestions and data are only for reference, not as product guarantee. It is up to the customer to decide whether the product is suitable or suitable for special use. We recommend that users first determine the suitability of our materials and recommendations before using them in large quantities.

以上建议及数据均来自我们认为可靠的资料。因此这些建议 及数据仅供参考,而不作为产品保证。应由客户决定产品是 否合适或适用特殊用途。我们建议用户在大量使用前,首先 确定我们的材料适用性和建议。

RH-GP600			
Property	Paramet er	Unit	Test Method
Color 颜色	灰色 Gray		Visual
Thermal Conductivity 导热系数	6.0	W/m.k	ASTM D5470
Base Material 基材			
Hardness 硬度	60	Shore 00	ASTM D2240
Thickness 厚度	0.5-6.0	mm	ASTM D374
Density 密度	3.2	g/cc	ASTM D792
Volume Resistivity 体积电阻率	10 ¹³	ohm-cm	ASTM D257
Dielectric Brekdown Voltage 击穿电压	>8	KV	ASTM D149
Permittivity 介电常数	6	@1M Hz	ASTM D150
Fire Rating 防火等级	V-0		UL94
Working Temperature 工作温度	-50~200	$^{\circ}\!$	
RoHS/REACH	Complian ce		

使用 ASTM D5470 测试夹具,记录值包括界面热阻,数值仅供参考。实际应用性能到所施加的表面粗糙度、平整度和压力。注: 厚度公差: ±10%, 硬度公差: ±5°, 颜色/厚度/硬度均可按顾客需求调试。

Applications

典型应用

Semiconductor heat sink半导体散热装置Graphics card, memory module显卡、记忆存储模块**Communication & power equipment通讯&电源设备**Vehicle navigator车载导航仪**LED television and lightingLED 电视和照明设备

Configurations Available

产品规格

**Flake products:300*400 mm or according to customer requirements 片状产品:300*400mm 或依照顾客要求

**Die-cutting products: according to customer requirements
 模切产品: 依照顾客要求

Storage & Transportation: store in a ventilated, cool and dry place, do not contact with open fire. This product is non-toxic and is stored and transported as non dangerous goods.

储存&运输: 贮存于通风、阴凉、干燥处,不要接触明火。本产品无毒,按非危险品贮存及运输。

Packaging: customized packaging according to customer needs.

包 装:根据客户需求定制包装。

Safety: please refer to material safety performance data (MSDS) of our company

安 全:请参阅本公司《材料安全性能数据 (MSDS)》

Period of validity: the product is valid for 24 months

有 效 期: 本产品有效期为 24 个月

REVVE®

深圳市睿玮新材料科技有限公司

电话 Tel: 0755 - 2340 0031 传真 Fax: 0755 - 3326 6039

广东省深圳市光明区圳美社区万代恒高新科技园 1号厂房 3楼